

PHENGUARD™ 935

OVERVIEW

- Place of origin: Indonesia
- Gloss level: Eggshell
- Dry to touch: 2 hours
- Number of components: 2
- Color: Pink

PRODUCT DETAIL

DESCRIPTION

Two-component, high-build, amine adduct-cured novolac phenolic epoxy coating

PRINCIPAL CHARACTERISTICS

- Second coat in the PHENGUARD tank coating system
- Excellent resistance to a wide range of organic acids, alcohols, edible oils, fats (regardless of free fatty acid content) and solvents
- Maximum cargo flexibility
- Low cargo absorption
- Good resistance to hot water
- Recognized corrosion control coating (Lloyd's register)
- Good application properties, resulting in a smooth surface

COLOR AND GLOSS LEVEL

- Pink
- Eggshell

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.7 kg/l (14.2 lb/US gal)
Volume solids	66 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 191.0 g/kg max. 315.0 g/l (approx. 2.6 lb/US gal)
Recommended dry film thickness	100 µm (4.0 mils)
Theoretical spreading rate	6.6 m ² /l for 100 µm (265 ft ² /US gal for 4.0 mils)
Dry to touch	2 hours
Overcoating Interval	Minimum: 24 hours Maximum: 21 days
Full cure after	See curing table

Shelf life	Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry
-------------------	--

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Previous coat (PHENGUARD 930) must be dry and free from any contamination
- The substrate must be perfectly dry before and during application of PHENGUARD 935

Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 10°C (50°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point

SYSTEM SPECIFICATION

- PHENGUARD TANK COATING SYSTEM – SYSTEM SHEET 3322
- HOT WATER RESISTANT SYSTEMS – SYSTEM SHEET 3141

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 88:12

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance and slower cure
- Thinner should be added after mixing the components

Induction time

Allow induction time before use

Mixed product induction time	
Mixed product temperature	Induction time
15°C (59°F)	20 minutes
20°C (68°F)	15 minutes
25°C (77°F)	10 minutes

Pot life: 4 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

Air spray

Recommended thinner: THINNER 91-92

Volume of thinner: 0 - 10%, depending on required thickness and application conditions

Nozzle orifice: 2.0 mm (approx. 0.079 in)

Nozzle pressure: 0.3 MPa (approx. 3 Bar; 44 p.s.i.)

Airless spray

Recommended thinner: THINNER 91-92

Volume of thinner: 0 - 10%, depending on required thickness and application conditions

Nozzle orifice: Approx. 0.46 – 0.53 mm (0.018 – 0.021 in)

Nozzle pressure: 15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Brush/roller

Recommended thinner: THINNER 91-92

Volume of thinner: 0 – 5%

Cleaning solvent: THINNER 90-53

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
100 µm (4.0 mils)	6.6 m ² /l (265 ft ² /US gal)
125 µm (5.0 mils)	5.3 m ² /l (212 ft ² /US gal)

Note: Maximum DFT when brushing: 60 µm (2.4 mils)

Overcoating interval for DFT up to 100 µm (4.0 mils)						
Overcoating with...	Interval	10°C (50°F)	15°C (59°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself and PHENGUARD 940	Minimum	36 hours	32 hours	24 hours	16 hours	12 hours
	Maximum	28 days	25 days	21 days	14 days	7 days

Note: Surface should be dry and free from any contamination

Curing time for DFT up to 100 µm (4.0 mils)	
Substrate temperature	Minimum curing time before transport of cargoes without note 4, 7, 8 or 11 and ballast water or tank test with sea water
10°C (50°F)	14 days
15°C (59°F)	14 days

20°C (68°F)	10 days
30°C (86°F)	7 days
40°C (104°F)	5 days

Notes:

- Minimum curing time of PHENGUARD tankcoating system before transport of cargoes with note 4, 7, 8 or 11: 3 months
- For detailed information on resistance and resistance notes, please refer to the latest issue of the cargo resistance list
- For transport of methanol and vinyl acetate monomer, a hot cure is required, which cannot be substituted by a service period of 3-months with non-aggressive cargoes
- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- The performance of the applied system strongly depends on the curing degree of the first coat at time of recoating. Therefore overcoating time between 1st and 2nd coat is extended in comparison between 2nd and 3rd coat (see overcoating details)

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	6 hours
20°C (68°F)	4 hours
30°C (86°F)	1.5 hours

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.