

SIGMACOVER™ 350

OVERVIEW

- Place of origin: Indonesia
- Gloss level: Semi-gloss
- Dry to touch: 2 hours
- Number of components: 2
- Color: Standard and custom colors, including aluminum

PRODUCT DETAIL

DESCRIPTION

Two-component, high-build polyamide cured anticorrosive epoxy primer/coating

PRINCIPAL CHARACTERISTICS

- Surface tolerant primer/coating for wide use in Marine and Protective Coatings
- Marine use: suitable on topsides, decks, superstructures and cargo holds
- Good impact and abrasion resistance
- Fast-curing
- Smooth film, easy to clean
- Compatible with various aged coatings
- Excellent corrosion resistance
- Resistant to splash and spillage of a wide range of chemicals

COLOR AND GLOSS LEVEL

- Standard and custom colors, including aluminum
- For Cargo holds gray (5177) and redbrown (6179) only
- Semi-gloss

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.4 kg/l (11.7 lb/US gal)
Volume solids	72 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 263.0 g/kg max. 361.0 g/l (approx. 3.0 lb/US gal)
Recommended dry film thickness	100 - 150 µm (4.0 - 6.0 mils) for airless spray
Theoretical spreading rate	5.8 m ² /l for 125 µm (231 ft ² /US gal for 5.0 mils) 4.8 m ² /l for 150 µm (192 ft ² /US gal for 6.0 mils)
Dry to touch	2 hours

Overcoating Interval	Minimum: 6 hours Maximum: 21 days
Full cure after	7 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to ISO-Sa2½ for excellent corrosion protection, blasting profile 40 – 70 µm (1.6 – 2.8 mils)
- Steel; blast cleaned to ISO-Sa2, blasting profile 40 – 70 µm (1.6 – 2.8 mils) or power tool cleaned to minimum ISO-St2 for good corrosion protection
- Coated steel; hydrojetted to VIS WJ2/3L
- Surface must be dry and free from any contamination
- Existing sound epoxy systems and most sound alkyd coating system; sufficiently roughened

Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point

SYSTEM SPECIFICATION

- SIGMACOVER 350: 2 x 125 µm (5.0 mils) DFT

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 80:20 (4:1)

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance
- Thinner should be added after mixing the components

Induction time: None

Pot life: 3 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

Air spray

Recommended thinner: THINNER 91-92

Volume of thinner: 5 - 10%, depending on required thickness and application conditions

Nozzle orifice: 1.8 – 2.0 mm (approx. 0.070 – 0.079 in)
Nozzle pressure: 0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

Airless spray

Recommended thinner: THINNER 91-92
Volume of thinner: 0 - 5%, depending on required thickness and application conditions
Nozzle orifice: Approx. 0.48 – 0.53 mm (0.019 – 0.021 in)
Nozzle pressure: 15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Brush/roller

Recommended thinner: THINNER 91-92
Volume of thinner: 0 – 5%
Cleaning solvent: THINNER 90-53

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
100 µm (4.0 mils)	7.2 m ² /l (289 ft ² /US gal)
125 µm (5.0 mils)	5.8 m ² /l (231 ft ² /US gal)
150 µm (6.0 mils)	4.8 m ² /l (192 ft ² /US gal)

Note: Maximum DFT when brushing: 100 µm (4.0 mils)

Overcoating interval for DFT up to 150 µm (6.0 mils)						
For application in Marine cargo holds and areas exposed to water immersion						
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	16 hours	9 hours	6 hours	4 hours	3 hours
	Maximum	1 month	1 month	21 days	14 days	7 days

Overcoating interval for DFT up to 150 µm (6.0 mils)						
For application in Marine areas subject to non-permanent exposure to splash water, seawater, spillage to chemicals etc.						
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself and various two-pack epoxy coatings	Minimum	16 hours	9 hours	6 hours	4 hours	3 hours
	Maximum	1 month	1 month	21 days	14 days	7 days
polyurethanes	Minimum	48 hours	30 hours	18 hours	9 hours	5 hours
	Maximum	1 month	21 days	14 days	7 days	3 days

Overcoating interval for DFT up to 150 µm (6.0 mils)

For application in atmospheric exposure and industrial PC

Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself and various two-pack epoxy coatings	Minimum	16 hours	9 hours	6 hours	4 hours	3 hours
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited	Unlimited
polyurethanes	Minimum	48 hours	30 hours	18 hours	9 hours	5 hours
	Maximum	6 months	6 months	3 months	1 month	1 month
various single pack coatings (such as alkyds and acrylics)	Minimum	24 hours	24 hours	16 hours	8 hours	5 hours
	Maximum	14 days	14 days	7 days	4 days	48 hours

Note: In cases of exposure to direct sunlight or when the surface is contaminated it is recommended that the surface be cleaned and roughened to ensure good adhesion of the subsequent coating.

Curing time for DFT up to 150 µm (6.0 mils)

Substrate temperature	Dry to touch	Dry to handle	Full cure
5°C (41°F)	12 hours	16 hours	25 days
10°C (50°F)	6 hours	9 hours	15 days
20°C (68°F)	2 hours	6 hours	7 days
30°C (86°F)	1 hour	4 hours	4 days
40°C (104°F)	1 hour	3 hours	48 hours

Notes:

- For cargo hold application: for full cure for hard angular cargoes, please contact your nearest PPG Protective & Marine Coatings sales office
- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- Should SIGMACOVER 350 or the total coating system (2 x 125 µm/2 x 5.0 mils) be applied in excess of the specified dry film thickness, then the time necessary to reach full cure will be increased

Pot life (at application viscosity)

Mixed product temperature	Pot life
15°C (59°F)	4 hours
20°C (68°F)	3 hours
30°C (86°F)	2 hours
40°C (104°F)	1 hour

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.