

# SIGMASHIELD™ 420

---

## OVERVIEW

- Place of origin: Indonesia
- Gloss level: Gloss
- Dry to touch: 3 hours
- Number of components: 2
- Color: Gray, redbrown (other colors available on request)

## PRODUCT DETAIL

### DESCRIPTION

Two-component, reinforced high solids polyamine adduct cured epoxy coating

### PRINCIPAL CHARACTERISTICS

- Coating for cargo tanks of bulk- or oil carriers and storage tanks
- Buildcoat for underwater- and boottop systems
- Excellent abrasion and impact resistance
- Outstanding (sea)water resistance
- Easy to clean

### COLOR AND GLOSS LEVEL

- Gray, redbrown (other colors available on request)
- Gloss

### BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.6 kg/l (13.4 lb/US gal)
Volume solids	81 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 153.0 g/kg UK PG 6/23(92) Appendix 3: max. 239.0 g/l (approx. 2.0 lb/US gal)
Recommended dry film thickness	125 - 200 µm (5.0 - 8.0 mils) depending on system
Theoretical spreading rate	5.4 m <sup>2</sup> /l for 150 µm (217 ft <sup>2</sup> /US gal for 6.0 mils) 4.1 m <sup>2</sup> /l for 200 µm (162 ft <sup>2</sup> /US gal for 8.0 mils)
Dry to touch	3 hours
Overcoating Interval	Minimum: 3.5 hours Maximum: 14 days
Full cure after	5 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

**RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES**

**Substrate conditions**

- Previous coat must be dry and free from any contamination

**Substrate temperature and application conditions**

- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
- Substrate temperature during application and curing down to 5°C (41°F) is acceptable

**SYSTEM SPECIFICATION**

- ANTICORROSIVE SYSTEMS FOR UNDERWATER AND BOOTTOP – SYSTEM SHEET 3101
- SYSTEMS FOR BOOTTOP AND TOPSIDE – SYSTEM SHEET 3102
- SYSTEMS FOR DECKS – SYSTEM SHEET 3103
- SYSTEMS FOR CARGO HOLDS – SYSTEM SHEET 3107

**INSTRUCTIONS FOR USE**

**Mixing ratio by volume: base to hardener 75:25 (3:1)**

- The temperature of the paint should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance and slower cure
- Thinner should be added after mixing the components

**Induction time:** None

**Pot life:** 1.5 hours

Note: See ADDITIONAL DATA – Pot life

**Air spray**

**Recommended thinner:** THINNER 91-92

**Volume of thinner:** 5 - 10%, depending on required thickness and application conditions

**Nozzle orifice:** 1.7 – 2.0 mm (approx. 0.070 – 0.079 in)

**Nozzle pressure:** 0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

**Airless spray**

**Recommended thinner:** THINNER 91-92

**Volume of thinner:** 0 - 10% for a DFT of 100 µm (4.0 mils); 0 - 5% for a DFT of 200 µm (8.0 mils)

**Nozzle orifice:** Approx. 0.53 – 0.69 mm (0.021 – 0.027 in)

**Nozzle pressure:** 15.0 MPa (approx. 150 bar; 2176 p.s.i.)

**Brush/roller**

**Recommended thinner:** THINNER 91-92

**Volume of thinner:** 0 – 5%

**Cleaning solvent:** THINNER 90-53

**ADDITIONAL DATA**

Spreading rate and film thickness	
DFT	Theoretical spreading rate
100 µm (4.0 mils)	8.1 m <sup>2</sup> /l (325 ft <sup>2</sup> /US gal)
150 µm (6.0 mils)	5.4 m <sup>2</sup> /l (217 ft <sup>2</sup> /US gal)
175 µm (7.0 mils)	4.6 m <sup>2</sup> /l (186 ft <sup>2</sup> /US gal)
200 µm (8.0 mils)	4.1 m <sup>2</sup> /l (162 ft <sup>2</sup> /US gal)

Note: Maximum DFT when brushing: 75 µm (3.0 mils)

Overcoating interval for DFT up to 150 µm (6.0 mils)						
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
epoxy coatings	Minimum	14 hours	7 hours	3.5 hours	2 hours	1.5 hours
	Maximum	28 days	28 days	14 days	7 days	4 days
polyurethanes	Minimum	22 hours	14 hours	10 hours	6 hours	4 hours
	Maximum	28 days	28 days	14 days	7 days	4 days

Note: Surface should be dry and free from any contamination

Curing time for DFT up to 150 µm (6.0 mils)			
Substrate temperature	Dry to handle	Service- water immersion	Full cure
5°C (41°F)	15 hours	10 days	17 days
10°C (50°F)	8 hours	7 days	14 days
20°C (68°F)	3.5 hours	5 days	7 days
30°C (86°F)	2 hours	4 days	5 days
40°C (104°F)	1.5 hours	3 days	3 days

**Notes:**

- For cargo hold application: for full cure for hard angular cargoes, please contact your nearest PPG Protective & Marine Coatings sales office
- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- Should SIGMASHIELD 420 or the total coating system (2 x 125 µm/2 x 5.0 mils) be applied in excess of the specified dry film thickness, then the time necessary to reach full cure will be increased

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	3 hours
20°C (68°F)	1.5 hours
30°C (86°F)	45 minutes

#### **SAFETY PRECAUTIONS**

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

#### **WORLDWIDE AVAILABILITY**

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.