

SIGMASHIELD™ 460

OVERVIEW

- Place of origin: Indonesia
- Gloss level: Gloss
- Dry to touch: 3 hours
- Number of components: 2
- Color: Black (other (light) colors on request)

PRODUCT DETAIL

DESCRIPTION

Two-component, high solids glass flake reinforced polyamine adduct epoxy coating

PRINCIPAL CHARACTERISTICS

- Excellent abrasion and impact resistance
- Suitable for use on ice-going vessels
- Excellent resistance to corrosion
- Long-term protection at areas subject to heavy wear and tear
- Resistant to splash and spillage of a wide range of chemicals
- Very low water permeability, due to glass flake barrier

COLOR AND GLOSS LEVEL

- Black (other (light) colors on request)
- Gloss

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.5 kg/l (12.5 lb/US gal)
Volume solids	81 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 165.0 g/kg max. 246.0 g/l (approx. 2.1 lb/US gal)
Recommended dry film thickness	250 - 400 µm (10.0 - 16.0 mils) depending on system
Theoretical spreading rate	3.2 m ² /l for 250 µm (130 ft ² /US gal for 10.0 mils) 2.0 m ² /l for 400 µm (81 ft ² /US gal for 16.0 mils)
Dry to touch	3 hours
Overcoating Interval	Minimum: 16 hours Maximum: 28 days
Full cure after	5 days

Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry
-------------------	--

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to ISO-Sa2½, blasting profile 40 – 70 µm (1.6 – 2.8 mils)
- Previous coat must be dry and free from any contamination

IMO-MSC.215(82) requirements for water ballast tanks

- Dust quantity rating "1 for dust size class "3", "4" or "5", lower dust size classes to be removed if visible on the surface to be coated without magnification (ISO 8502-3:1992)

Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point

SYSTEM SPECIFICATION

- ANTICORROSIVE SYSTEMS FOR UNDERWATER AND BOOTTOP – SYSTEM SHEET 3101
- SYSTEMS FOR BOOTTOP AND TOPSIDE – SYSTEM SHEET 3102

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 75:25 (3:1)

- The temperature of the paint should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance and slower cure
- Very good mechanical mixing of base and hardener is essential
- Thinner should be added after mixing the components
- Filters should be removed from spray equipment

Induction time: None

Pot life: 1.5 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

Air spray

Recommended thinner: THINNER 91-92

Volume of thinner: 5 - 10%, depending on required thickness and application conditions

Nozzle orifice: 1.5 – 2.0 mm (approx. 0.060 – 0.079 in)

Nozzle pressure: 0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

Airless spray

Recommended thinner: THINNER 91-92

Volume of thinner: 0 - 5%, depending on required thickness and application conditions

Nozzle orifice: Approx. 0.53 – 0.79 mm (0.021 – 0.031 in)

Nozzle pressure: 19.0 - 22.5 MPa (approx. 190 - 225 bar; 2756 - 3264 p.s.i.)

Brush/roller

- Brush application only
- Only for touch-up and repair
- Due to thixotropy, it is difficult to obtain a smooth film by brush, although this does not affect performance

Cleaning solvent: THINNER 90-53

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
250 µm (10.0 mils)	3.2 m ² /l (130 ft ² /US gal)
400 µm (16.0 mils)	2.0 m ² /l (81 ft ² /US gal)

Notes:

- Maximum DFT when brushing: 80 µm (3.1 mils)
- Maximum recommended dft for complex structures is 250 µm (10.0 mils)

Overcoating interval for DFT up to 400 µm (16.0 mils) itself						
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	48 hours	32 hours	16 hours	12 hours	8 hours
	Maximum	28 days	28 days	28 days	14 days	7 days

Note: Surface should be dry and free from chalking and contamination

Curing time for DFT up to 400 µm (16.0 mils)			
Substrate temperature	Dry to touch	Dry to handle	Service- water immersion
5°C (41°F)	16 hours	30 hours	14 days
10°C (50°F)	8 hours	16 hours	10 days
20°C (68°F)	3 hours	8 hours	5 days
30°C (86°F)	2 hours	5 hours	4 days
40°C (104°F)	1 hour	3 hours	3 days

Note: Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	3 hours
20°C (68°F)	1.5 hours
30°C (86°F)	45 minutes

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.